



Performance & Test Results: ecotile 500/ESD has been independently tested:

- Surface Resistivity: $2.2 \times 10^4 \Omega$ to $3 \times 10^6 \Omega$
- Resistance to ground: $2.9 \times 10^4 \Omega$ to $5.7 \times 10^5 \Omega$
- Walking Test: <100V
- Static Decay at 15% humidity: 0.01sec

The test results guarantee that ecotile 500/ESD complies with British Standard BS EN 61340-5:2001 and IEC 61340.

	5mm	7mm
Dimensions:	500mm x 500mm	500mm x 500mm
Thickness:	4.5mm +/- 0.3mm	6.8mm +/- 0.3mm
Weight:	5.44kgs/m ²	8.86kgs/m ²
Guarantee:	10 Years	10 Years
Anticipated Service Life:	25 Years +	25 Years +
Material:	PVC	PVC
Joint:	Dovetail	Dovetail

- Offices
- Server Rooms
- Electronic Factories
- Cleanrooms
- Data Centres
- Healthcare Environments



EN/ISO 61340/5, EN 1081,
EN1815 & EN6356
ESD Flooring - Resistance to Ground



EN/ISO 61340/5, EN 1081,
EN1815 & EN6356
ESD Flooring - Surface Resistance

Slip Resistance:	EN 14041:2004 DIN 51130:2004	Smooth Pass R10
Fire Performance:	BS 476: Part 7 DIN 13501: 2007	Class 1 Spread of Flame Bfl-S1 Does not support combustion
Stain Resistance:	EN 423	Good
Abrasion Wear Resistance:	EN 13845 EN 649	50K Cycles Group T
Mechanical Resistance:	DIN 53516	17N/mm ²
Resistance to Hot Objects/Solder:		Good
Thickness of Wear Layer:	EN 429	6 to 10mm
Hardness:	ISO 868	89-92 Shore A
Impact Resistance:	EN 13329-549	549kg/cm ²
Noise Reduction:	EN 140-8	>46db
Determination of Length, Squareness & Straightness:	BS EN 428:1993	<0.13% / 0.5mm max.
Chemical Resistance:	EN 13529	Good resistance to most commonly used chemicals. Common acid oils & gas oil - No deterioration / Not Resistant to prolonged contact
Colour Fastness:	EN 50105-BO21	5

per ulteriori informazioni contattate:

FORMAR SRL
VIA ACHILLE GRANDI 26
15033 CASALE MONFERRATO (AL)
ITALIA
TEL. 0142 455075
FAX 0142 74834
WWW.FORMAR.IT