




altro

Altro Whiterock White™



Order No.

Bestell-Nr.

Número de pedido

W103/2100

W103

W103/2750

W104

Sheet size

Abmessungen

Dimensiones

2100 x 1220 mm

2500 x 1220 mm

2750 x 1220 mm

3000 x 1220 mm


LRV 89

For more colourful solutions / Mehr Möglichkeiten für Ihre Projekte
Añade color a tus proyectos

Altro Whiterock Satins™

Available in 27 shades / in 27 Farben verfügbar

Disponible en 27 tonalidades



Altro Whiterock Chameleon™

Available in 16 shades / in 16 Farben verfügbar

Disponible en 16 tonalidades



Typical applications / Typische Anwendungsbereiche / Zonas de instalación recomendadas

Accident and emergency, critical care. Commercial, social, student kitchens. Laboratories, test areas. Laundries, mortuaries. Bathrooms.

Unfall-, Notfall- und Intensivmedizin. Gewerbliche Küchen, Gemeinschafts- und Pantryküchen. Labore, Testbereiche. Wäschereien, Leichenhallen. Badezimmer.

Salas de emergencias y cuidados críticos. Cocinas Industriales. Laboratorios clínicos, áreas de extracción. Lavanderías, tanatorios, áreas de medicina ambulatoria. Baños.

Technical information / Technische Informationen / Información técnica / Information technique

Surface finish	Oberfläche	Acabado de la superficie	Finition	Satin, Satin, Satinado, Satin
Thickness	Gesamtstärke	Espesor	Epaisseur	2.5 mm
Size	Plattengröße	Dimensiones	Dimension	2100 mm x 1220 mm 2500 mm x 1220 mm 2750 mm x 1220 mm 3000 mm x 1220 mm
Weight	Flächengewicht	Peso	Poids	3600 g/m²
Maximum service temperature	Max. Betriebstemperatur	Temperatura máxima de uso	Température maximale supportée	60°C
E-modulus of elasticity	Bruchfestigkeit	Módulos de elasticidad	Module d'élasticité	ISO 527 2980 MPa
Notched impact resistance	Kratz- und Kerbzähigkeit	Resistencia al impacto	Résistance à l'impact	ISO 179/1ea 9.5 KJ/m²
Flexural strength	Biegefestigkeit	Resistencia a la flexión	Résistance à la flexion	ISO 178 78 MPa
Tensile strength	Zugfestigkeit	Resistencia a la tensión	Résistance à la traction	ISO 527 53 MPa
Shore D hardness	Shore D-Härte	Dureza (Shore D)	Dureté Shore D	ISO 868 75
Thermal conductivity- 'K Value'	Wärmeleitung	Conductividad térmica	Conductivité thermique	EN 12524 0.17 W/mK
Water absorption	Wasserabsorption	Absorción de agua	Imperméabilité	ISO 62 ≤ 0.1 %
Moisture vapour transmission rate (MVTR)	Wasserdampfdurchlässigkeitsrate (MVTR)	Rango de transmisión de humedad de vapor (MVTR)	Taux de transmission de vapeur d'eau	ASTM E96 ≤ 0.12 g/m²/24h
Fire performance	Brandverhalten	Resistencia al fuego	Réaction au feu	EN 13501-1 B- s3, d0



Altro Limited a company certified by SGS to ISO 9001 and ISO 14001.



2812
EN 15102



1121
EN 15102



EN 15804 SD207
EPD No.: 000338



Recowall
Altro wall cladding recycling scheme

Installation and maintenance / Montage und Pflege / Instalación y mantenimiento

Please refer to Altro installation and maintenance instructions. Failure to follow these instructions can affect product performance and may affect or invalidate Altro's product guarantee. Technical information on installation and maintenance (including cleaning and staining) can be found at www.altro.com

Die Nichtbeachtung der Altro Verlege- und Pflegeanleitungen kann die Leistung des Produkts beeinträchtigen und zum Erlöschen der Produktgarantie von Altro führen. Technische Informationen zur Verlegung und Pflege (z. B. Reinigung und Fleckenbehandlung) finden Sie unter www.altro.com

Consulte las instrucciones de instalación y mantenimiento de Altro. El incumplimiento de estas instrucciones puede afectar al rendimiento del producto y puede afectar o invalidar la garantía del producto de Altro. Encontrará información técnica sobre la instalación y el mantenimiento (incluida la limpieza periódica y específica) en www.altro.com

Light Reflectance Values measured in accordance with BS 8493:2008. Exact material match with samples cannot be guaranteed.

LRV = light reflectance value

Lichtreflexionsgrad (LRV) gemäß BS 8493:2008. Eine exakte Übereinstimmung des Materials mit Mustern kann nicht garantiert werden.

LRV = Lichtreflexionsgrad

Los Valores de Reflectancia de la luz se miden de acuerdo con BS 8493:2008. Las muestras no pueden garantizar un color exacto.

LRV = Valor de reflectancia de la Luz



Altro, Designed for possibilities. Made for people.. Altro Whiterock White, Altro Whiterock Satins and Altro Whiterock Chameleon are trademarks of Altro Limited.

United Kingdom ☎ +44 (0) 1462 707 700 ✉ enquiries@altro.com

Germany ☎ +49 (0) 340 6500 400 ✉ anfrage@altro.de

France ☎ +33 1 57 32 92 30 ✉ france@altro.com

Australia ☎ +61 3 9764 5666 ✉ info@asf.com.au

Spain ☎ +34 91 549 5230 ✉ suelos@altro.com